

SUPER STRONG SUPER SULIT!

PREMIUM GRADE



- Smoothens masonry surfaces
- Resistant to hairline cracks
- Superior strength and durability
- Alkali-resistant
- Provides outstanding adhesion to water-based paint systems
- Faster curing compared to traditional plastered walls



MONDO
SKIMCOAT
Superfine White SK-1

PREMIUM GRADE

Is a specially formulated free-flowing white powder to be mixed with water to form a paste that is used to fill up cracks and achieve smooth and even concrete surfaces. It is also sag resistant - perfect for ceiling, beams and other overhead applications.

FEATURES

- Super Adhesion
- Superior Strength and Durability
- Resistant to hairline cracks
- Saves time and money!

SURFACE PREPARATION

- Ensure that surface is free of dust, oil, laitance, paint, curing compound, algae, mildew, and other contaminants.
- Scrape off cement residue, loose material, and sand away rough edges for a smooth surface.
- Surface must be cured 5-7 days before application.

PRODUCT PREPARATION

- Blend until the mixture is lump-free and homogenous. Use an electric mixer for bigger volumes of mixture.

PRODUCT APPLICATION

- Lightly mist concrete surface with water, or dampen with a wet cloth before applying.
- Apply **MONDO™ SKIMCOAT™ SK-1** with the use of a clean stainless or wooden trowel. Recommended skimcoat thickness for application is 0.50-2mm.

PAINT APPLICATION

- Lightly sand the coated surface to prepare it for paint.
- Wipe off dust.
- Apply the recommended painting system.



MONDO
SKIMCOAT
Acrylic Skimcoat SK-2

PREMIUM GRADE

Is specially formulated rendering paste that can easily be mixed with cement to fill up cracks to achieve smooth and even concrete surfaces. It is resistant to hairline cracks and exhibits excellent adhesion making it ideal as a finishing plaster for concrete walls.

FEATURES

- Smoothens masonry surfaces
- Resistant to hairline cracks
- Outstanding Strength and Durability
- Alkali Resistant
- Fast and Easy Application

SURFACE PREPARATION

- Ensure that surface is free of dust, oil, laitance, paint, curing compound, algae, mildew, and other contaminants.
- Scrape off cement residue, loose material, and sand away rough edges for a smooth surface.
- Surface must be cured 5-7 days before application.

PRODUCT PREPARATION

- Sieve the cement to eliminate agglomerates and lumps.
- Mix 1 part **MONDO™ SKIMCOAT™ SK-2** with ½ to 1 part sieved cement, with adjustments as needed.
- Blend until the mixture is lump-free and homogenous. Use an electric mixer for bigger volumes of mixture.
- * Do NOT add water while mixing, or after the desired consistency is achieved.

PRODUCT APPLICATION

- Lightly mist concrete surface with water, or dampen with a wet cloth before applying.
- Apply **MONDO™ SKIMCOAT™ SK-2** with the use of a clean stainless trowel.
- Allow a minimum of 24 hours, depending on the thickness and atmospheric conditions, before applying paint or wallpaper.

PAINT APPLICATION

- Lightly sand the coated surface to prepare it for paint.
- Apply the recommended painting system.



MONDO
SKIMCOAT
Acrylic Skimcoat SK-3

PREMIUM GRADE

Is a one component ready to use acrylic skim coat paste for interior and exterior use.

FEATURES

- Ready to use
- Easy to apply and sand
- Resistant to hairline cracks
- Achieves a very smooth finish
- Sag Resistant
- Excellent adhesion to masonry surfaces

SURFACE PREPARATION

- Ensure the surface is structurally sound and clean from dust, oil, algae, mildew, etc.
- Remove algae and mildew with an appropriate cleaner and wash with soap and water
- Scrape off loosely adhering material with a wire brush or scraper
- New concrete must be cured at least 7 days
- Damage concrete surfaces, seams and rockpockets that exceeds 3mm must be treated before application

PRODUCT PREPARATION

- **MONDO™ ACRYLIC SKIMCOAT™ SK-3** is a ready to use paste. Do not dilute with water.

APPLICATION

- Apply One (1) coat with a stainless steel trowel
- Allow sufficient drying time before applying the second coat in order to prevent drawn off of the previous coat or until required thickness is obtained. Maximum thickness is 0.3-4mm.
- Use sandpaper to polish the surface. Allow curing time of 24 hours before painting.

Davies Paints Philippines, Inc.

1415 A. Sandoval Ave., cor. Mercedes Ave., San Miguel, Pasig City 1600, Philippines